

# Larssön CLEAR EPOXY



## 4 Min EPOXY ADHESIVE

### DESCRIPTION:

LARSSÖN CLEAR EPOXY is fast setting, non-shrinking extra strong clear epoxy adhesive. Is heat, water, and chemical resistant. Excellent for bonding uses metal, wood and masonry. No solvent nor VOC, not flammable.

### FEATURES:

- Easy to use, one to one mixing ratio
- Setting in 4 minutes
- Strong bonding strength!
- Chemical and heat resistance
- Water Proof
- Non-shrinkage
- Paintable and drillable after cured.

### USES:

An adhesive or emergency repairing material that has excellent adhesion to all metals, fiberglass, wood, porcelain, masonry and most or rigid plastics.

**WE RECOMMEND PRELIMINARY COMPATIBILITY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS**

### NOT RECOMMENDED FOR:

Not for: PE, PP AND PTFE.

### APPLICATION:

- Surface must be clean, dry and free from dirt, grease, oil or water
- Apply equal amount of resin and hardener onto any discarded surface and mix
- Apply mixture to surface beign repair and remove excess material
- Replace cap immediately after use. Store in a cool dry place

### CURING TIME:

Will cure in approximately 3 - 5 minutes under room temperature

### SPECIFICATION:

FORM	LIQUID
COLOUR	CLEAR CHARACTERISTIC
ODOUR	ODOUR 1.16 ± 0.05 (RESIN)
DENSITY	1.13 ± 0.03 (HARDENER)
	6,000 – 8,000 CPS (RESIN)
VISCOSITY	10,000 – 15,000 CPS (HARDENER)
HARDNESS, SHORE D	70 MINIMUM
SERVICE TEMPERATURE	+15°C TO 100°C
SHELF LIFE	24 MONTHS

\*Mixing ratio (by volume): 1 part Resin to 1 part Hardener

### STORAGE:

Material should be stored in a dry and cool place, between +5°C TO +30°C.

### CAUTION:

- Avoid breathing vapors
- Skin corrosion or irritation
- Wash hands thoroughly after handling
- Toxic to aquatic life with long lasting effects
- Contaminated work clothing should not be allowed out of the workplace
- Avoid release to the environment
- Wear protective gloves, clothing, eyes and face protection
- Store in a secure and well-ventilated place

\* For severe cases get medical attention

*This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.*