

Larssön 699+ Grey Plus Silicone

RTV GASKET MAKER (NEUTRAL)



DESCRIPTION:

Larssön 699+ Grey Plus Silicone is a RTV gasket maker with a reforced formula that allows it to have an outstanding performance in high temperatures .

FEATURES:

- OXIME
- Non corrosive
- Low Odor
- Sensor safe
- Resistant to oil, water and antifreeze
- 750° F (399°C)

USES:

- High temperature resistant gasket and joint sealing.
- Assemblies of glass, porcelain, coated metal, epoxy and polyester panels, aluminium and finished wood.

WE RECOMMEND PRELIMINARY COMPATIBILITY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS

NOT RECOMMENDED FOR:

Not paintable
 Not for: PE, PP, PTFE AND BITUMINOUS SURFACE.
 Not for: Parts in contact with gasoline.

APPLICATION:

- Remove old gasket material from surfaces thoroughly
- Clean surface with residue-free solvent and allow surface to dry
- Cut nozzle to desire size
- Apply evenly around all the surface you want to seal
- Let rest 10 to 15 minutes
- Tighten to the required torque, do not overtighten
- Clean off excess

CURING TIME:

Will tack free in approximately 15 minutes and will cure to a depth of 13mm within 7 days

SPECIFICATION:

CURING SYSTEM	NEUTRAL (OXIME) NON-SAGGING PASTE OXIME
APPEARANCE ODOUR	SMELL
SPECIFIC GRAVITY	1.40 ± 0.05
SHORE A HARDNESS	38 APPROX.
ELONGATION TENSILE	200% APPROX.
STRENGTH TACK FREE	2.0 MPa APPROX.
TIME	15 MINUTES
APPLICATION TEMP.	-20°C TO 50°C
SERVICE	-40°C TO 371°C.
TEMPERATURE	12 MONTHS
SHELF LIFE	

STORAGE:

Material should be stored in a dry and cool place, between +50C TO +300C.

CAUTION:

- Skin corrosion or irritation
- Serious eye damage or eye irritation when in contact
- Wash thoroughly after handling
- Wear protective gloves, clothing, eyes and face protection

*In case of skin or eye contact, wash with plenty of water and soap. For severe cases get medical attention

This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.